



Kisling AG

**Motorenstrasse 102
CH-8620 Wetzikon**

Telefon +41 (0)58 272 01 01
Telefax +41 (0)58 272 01 03

info@kisling.com
www.kisling.com

TECHNICAL DATA SHEET ergo.® 4052

Thread Locker, medium strength

Description

Medium strength product with excellent resistance against chemicals and temperature. Cures very fast, even on galvanised surfaces and on stainless or high alloyed steel. Certified acc. to **DVGW** (EN 751-1) and to **NSF ANSI 61** for use in commercial and residential drinking water systems not exceeding +82°C. **NSF P1** listed for use in food processing areas. **Complies with the guide formulation of the German Federal Environment Agency, published 2016, February 11th, for use in contact with drinking water.** **According to DVGW TRGI 2008, In Germany not allowed for use in household gas-installations.**

Attention:

If used as sealant against water, please observe and follow the special handling instructions for pipe-sealants.

Physical Properties (liquid product)

Chemical Base:	Diester of Methacrylic Acid
Colour:	blue / fluorescent
Viscosity acc. to Brookfield RVT at 25°C: spindle 3, 2.5 rpm 20 rpm	4000 – 9000 mPas 1500 – 3000 mPas
Density at 25°C:	1.12 g/cm ³
Max. thread diameter:	M 36
Max. gap filling:	0.25 mm
Flash point:	> 100°C
Shelf life:	1 year at ≤ 25°C

Physical Properties (cured product)

Measured on M10 x 20 bolt - grade 8.8 black phosphatized - nut 0.8d (no on-torque)

Initial strength after:	5 – 15 minutes	
Functional strength after:	0.5 – 1 hour	
Final strength after:	1 – 3 hours	
Loose-break torque:	~ 21 Nm (M10)	DIN 54454
Prevailing torque:	~ 10 Nm (M10)	
Shear strength:	~ 20 N/mm ²	DIN 54452

Thermal range: - 55°C up to +150°C

WARRANTY INFORMATION - PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that KISLING products are safe, effective, and fully satisfactory for the intended end use. KISLING sole warranty is that the product will meet the KISLING sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. KISLING specifically disclaims any other express or implied warranty of fitness for a particular purpose or merchantability. Unless KISLING provides you with a specific, duly signed endorsement of fitness for use, KISLING disclaims liability for any incidental or consequential damages. Suggestions of uses should not be taken as inducements to infringe any particular patent.